

School on Wannier90 v3.0: new features and applications

25-27th March 2020 – Virtual Edition

Electron-phonon coupling and the EPW code

Roxana Margine

Department of Physics, Applied Physics, and Astronomy
Binghamton University - State University of New York


Lecture Summary

- Manifestations of the electron-phonon interaction
- The electron-phonon matrix element
- Brillouin-zone integrals and Wannier interpolation
- Migdal-Eliashberg theory of superconductivity
- Boltzmann transport equation

Why electron-phonon interactions are important?

Some manifestations of electron-phonon interactions


Electron mobility in monolayer and bilayer MoS₂



Nano Lett. 13, 4212 (2013)


Some manifestations of electron-phonon interactions

Electron mobility in monolayer and bilayer MoS₂



Nano Lett. 13, 4212 (2013)


Phonon-assisted optical absorption in silicon



Prog. Photovolt. Res. Appl. 3, 189 (1995)


Some manifestations of electron-phonon interactions

Electron mobility in monolayer and bilayer MoS₂




Nano Lett. 13, 4212 (2013)

Phonon-assisted optical absorption in silicon



Prog. Photovolt. Res. Appl. 3, 189 (1995)


Superconductivity in compressed LaH_{10±x}



PRL 122, 027001 (2019)


Some manifestations of electron-phonon interactions

Electron mobility in monolayer and bilayer MoS₂




Nano Lett. 13, 4212 (2013)

Phonon-assisted optical absorption in silicon




Prog. Photovolt. Res. Appl. 3, 189 (1995)

Superconductivity in compressed LaH_{10±x}



PRL 122, 027001 (2019)

Photoluminescence in hybrid perovskites



Nat. Commun. 7, 11755 (2016)


The electron-phonon matrix element

The electron-phonon matrix element

$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \langle u_{m\mathbf{k}+\mathbf{q}} | \Delta_{\mathbf{q}\nu} v_{\text{SCF}} | u_{n\mathbf{k}} \rangle_{\text{uc}}$$

The electron-phonon matrix element

$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \langle u_{m\mathbf{k}+\mathbf{q}} | \Delta_{\mathbf{q}\nu} v_{\text{SCF}} | u_{n\mathbf{k}} \rangle_{\text{uc}}$$




Lattice-periodic part of wavefunction

The electron-phonon matrix element

Variation of the Kohn-Sham potential



$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \langle u_{m\mathbf{k}+\mathbf{q}} | \Delta_{\mathbf{q}\nu} v_{\text{SCF}} | u_{n\mathbf{k}} \rangle_{\text{uc}}$$




Lattice-periodic part of wavefunction

The electron-phonon matrix element

Variation of the Kohn-Sham potential



$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \langle u_{m\mathbf{k}+\mathbf{q}} | \Delta_{\mathbf{q}\nu} v_{\text{SCF}} | u_{n\mathbf{k}} \rangle_{\text{uc}}$$



Lattice-periodic part of wavefunction

$$\Delta_{\mathbf{q}\nu} v_{\text{SCF}} = \sum_{\kappa\alpha p} e^{-i\mathbf{q}\cdot(\mathbf{r}-\mathbf{R}_p)} \sqrt{\frac{\hbar}{2M_\kappa\omega_{\mathbf{q}\nu}}} e_{\kappa\alpha,\nu}(\mathbf{q}) \frac{\partial V_{\text{SCF}}(\mathbf{r})}{\partial \tau_{\kappa\alpha p}}$$

κ Atom in the unit cell

α Cartesian direction


p Unit cell in the equivalent supercell

The electron-phonon matrix element

Variation of the Kohn-Sham potential



$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \langle u_{m\mathbf{k}+\mathbf{q}} | \Delta_{\mathbf{q}\nu} v_{\text{SCF}} | u_{n\mathbf{k}} \rangle_{\text{uc}}$$



Lattice-periodic part of wavefunction

$$\Delta_{\mathbf{q}\nu} v_{\text{SCF}} = \sum_{\kappa\alpha p} e^{-i\mathbf{q}\cdot(\mathbf{r}-\mathbf{R}_p)} \sqrt{\frac{\hbar}{2M_{\kappa}\omega_{\mathbf{q}\nu}}} e_{\kappa\alpha,\nu}(\mathbf{q}) \frac{\partial V_{\text{SCF}}(\mathbf{r})}{\partial \tau_{\kappa\alpha p}}$$



Zero-point amplitude

κ Atom in the unit cell

α Cartesian direction


p Unit cell in the equivalent supercell

The electron-phonon matrix element

Variation of the Kohn-Sham potential



$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \langle u_{m\mathbf{k}+\mathbf{q}} | \Delta_{\mathbf{q}\nu} v_{\text{SCF}} | u_{n\mathbf{k}} \rangle_{\text{uc}}$$



Lattice-periodic part of wavefunction

$$\Delta_{\mathbf{q}\nu} v_{\text{SCF}} = \sum_{\kappa\alpha p} e^{-i\mathbf{q}\cdot(\mathbf{r}-\mathbf{R}_p)} \sqrt{\frac{\hbar}{2M_\kappa\omega_{\mathbf{q}\nu}}} e_{\kappa\alpha,\nu}(\mathbf{q}) \frac{\partial V_{\text{SCF}}(\mathbf{r})}{\partial \tau_{\kappa\alpha p}}$$



Zero-point amplitude



Phonon polarization

κ Atom in the unit cell

α Cartesian direction


p Unit cell in the equivalent supercell

The electron-phonon matrix element

Variation of the Kohn-Sham potential



$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \langle u_{m\mathbf{k}+\mathbf{q}} | \Delta_{\mathbf{q}\nu} v_{\text{SCF}} | u_{n\mathbf{k}} \rangle_{\text{uc}}$$



Lattice-periodic part of wavefunction

$$\Delta_{\mathbf{q}\nu} v_{\text{SCF}} = \sum_{\kappa\alpha p} e^{-i\mathbf{q}\cdot(\mathbf{r}-\mathbf{R}_p)} \sqrt{\frac{\hbar}{2M_\kappa\omega_{\mathbf{q}\nu}}} e_{\kappa\alpha,\nu}(\mathbf{q}) \frac{\partial V_{\text{SCF}}(\mathbf{r})}{\partial \tau_{\kappa\alpha p}}$$



Zero-point amplitude



Phonon polarization



Displacement of a single ion

κ Atom in the unit cell

α Cartesian direction


p Unit cell in the equivalent supercell

The electron-phonon matrix element

Variation of the Kohn-Sham potential



$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \langle u_{m\mathbf{k}+\mathbf{q}} | \Delta_{\mathbf{q}\nu} v_{\text{SCF}} | u_{n\mathbf{k}} \rangle_{\text{uc}}$$



Lattice-periodic part of wavefunction

Incommensurate modulation



$$\Delta_{\mathbf{q}\nu} v_{\text{SCF}} = \sum_{\kappa\alpha p} e^{-i\mathbf{q}\cdot(\mathbf{r}-\mathbf{R}_p)} \sqrt{\frac{\hbar}{2M_\kappa\omega_{\mathbf{q}\nu}}} e_{\kappa\alpha,\nu}(\mathbf{q}) \frac{\partial V_{\text{SCF}}(\mathbf{r})}{\partial \tau_{\kappa\alpha p}}$$



Zero-point amplitude



Phonon polarization



Displacement of a single ion

κ Atom in the unit cell
 α Cartesian direction
 p Unit cell in the equivalent supercell

Brillouin-zone integrals

Example: electron lifetimes in metals, adiabatic approximation

$$\frac{1}{\tau_{n\mathbf{k}}} = 2k_{\text{B}}T \frac{2\pi}{\hbar} \sum_{m\nu} \int_{\text{BZ}} \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{|g_{nm\nu}(\mathbf{k}, \mathbf{q})|^2}{\hbar\omega_{\mathbf{q}\nu}} \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}})$$

Brillouin-zone integrals

Example: electron lifetimes in metals, adiabatic approximation

$$\frac{1}{\tau_{n\mathbf{k}}} = 2k_{\text{B}}T \frac{2\pi}{\hbar} \sum_{m\nu} \int_{\text{BZ}} \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{|g_{nm\nu}(\mathbf{k}, \mathbf{q})|^2}{\hbar\omega_{\mathbf{q}\nu}} \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}})$$

- The **integral** over the Brillouin zone can require up to 100K $\mathbf{q}$ -vectors

Brillouin-zone integrals

Example: electron lifetimes in metals, adiabatic approximation

$$\frac{1}{\tau_{n\mathbf{k}}} = 2k_{\text{B}}T \frac{2\pi}{\hbar} \sum_{m\nu} \int_{\text{BZ}} \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{|g_{nm\nu}(\mathbf{k}, \mathbf{q})|^2}{\hbar\omega_{\mathbf{q}\nu}} \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}})$$

- The **integral** over the Brillouin zone can require up to 100K $\mathbf{q}$ -vectors
- Each **$\mathbf{q}$ -vector** requires a separate DFPT calculation

Brillouin-zone integrals

Example: electron lifetimes in metals, adiabatic approximation

$$\frac{1}{\tau_{n\mathbf{k}}} = 2k_{\text{B}}T \frac{2\pi}{\hbar} \sum_{m\nu} \int_{\text{BZ}} \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{|g_{nm\nu}(\mathbf{k}, \mathbf{q})|^2}{\hbar\omega_{\mathbf{q}\nu}} \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}})$$

- The **integral** over the Brillouin zone can require up to 100K $\mathbf{q}$ -vectors
- Each $\mathbf{q}$ -vector requires a separate DFPT calculation
- A new integral must be evaluated for every **$\mathbf{k}$ -vector**

Wannier interpolation of electron-phonon matrix elements

Wannier functions


$$w_{mp}(\mathbf{r}) = \frac{1}{N_p} \sum_{n\mathbf{k}} e^{-i\mathbf{k}\cdot\mathbf{R}_p} U_{nm\mathbf{k}} \psi_{n\mathbf{k}}(\mathbf{r})$$

Wannier interpolation of electron-phonon matrix elements

Wannier functions

$$w_{mp}(\mathbf{r}) = \frac{1}{N_p} \sum_{n\mathbf{k}} e^{-i\mathbf{k}\cdot\mathbf{R}_p} U_{nm\mathbf{k}} \psi_{n\mathbf{k}}(\mathbf{r})$$

$$\psi_{n\mathbf{k}}(\mathbf{r}) = e^{i\mathbf{k}\cdot\mathbf{r}} u_{n\mathbf{k}}(\mathbf{r})$$




Wannier interpolation of electron-phonon matrix elements

Wannier functions

$$w_{mp}(\mathbf{r}) = \frac{1}{N_p} \sum_{n\mathbf{k}} e^{-i\mathbf{k}\cdot\mathbf{R}_p} U_{nm\mathbf{k}} \psi_{n\mathbf{k}}(\mathbf{r})$$

$$\psi_{n\mathbf{k}}(\mathbf{r}) = e^{i\mathbf{k}\cdot\mathbf{r}} u_{n\mathbf{k}}(\mathbf{r})$$




Wannier interpolation of electron-phonon matrix elements

Wannier functions

$$w_{mp}(\mathbf{r}) = \frac{1}{N_p} \sum_{n\mathbf{k}} e^{-i\mathbf{k}\cdot\mathbf{R}_p} U_{nm\mathbf{k}} \psi_{n\mathbf{k}}(\mathbf{r})$$

$$\psi_{n\mathbf{k}}(\mathbf{r}) = e^{i\mathbf{k}\cdot\mathbf{r}} u_{n\mathbf{k}}(\mathbf{r})$$



$$\psi_{n\mathbf{k}}(\mathbf{r}) = \sum_{mp} e^{i\mathbf{k}\cdot\mathbf{R}_p} U_{mn\mathbf{k}}^\dagger w_{mp}(\mathbf{r})$$

Wannier interpolation of electron-phonon matrix elements

$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \sqrt{\frac{\hbar}{2M_{\kappa}\omega_{\mathbf{q}\nu}}} \sum_{pp'} e^{i(\mathbf{k}\cdot\mathbf{R}_p + \mathbf{q}\cdot\mathbf{R}_{p'})} \\ \times \sum_{m'n'\kappa\alpha} U_{mm'\mathbf{k}+\mathbf{q}} g_{m'n'\kappa\alpha}(\mathbf{R}_p, \mathbf{R}_{p'}) U_{n'n\mathbf{k}}^{\dagger} e_{\kappa\alpha,\nu}(\mathbf{q})$$

Wannier interpolation of electron-phonon matrix elements


$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \sqrt{\frac{\hbar}{2M_\kappa\omega_{\mathbf{q}\nu}}} \sum_{pp'} e^{i(\mathbf{k}\cdot\mathbf{R}_p + \mathbf{q}\cdot\mathbf{R}_{p'})} \\ \times \sum_{m'n'\kappa\alpha} U_{mm'\mathbf{k}+\mathbf{q}} g_{m'n'\kappa\alpha}(\mathbf{R}_p, \mathbf{R}_{p'}) U_{n'n\mathbf{k}}^\dagger e_{\kappa\alpha,\nu}(\mathbf{q})$$

$$g_{mn\kappa\alpha}(\mathbf{R}_p, \mathbf{R}_{p'}) = \langle w_{m0}(\mathbf{r}) | \frac{\partial V_{\text{SCF}}}{\partial \tau_{\kappa\alpha}}(\mathbf{r} - \mathbf{R}_{p'}) | w_{n0}(\mathbf{r} - \mathbf{R}_p) \rangle_{\text{sc}}$$

Wannier interpolation of electron-phonon matrix elements

$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \sqrt{\frac{\hbar}{2M_{\kappa}\omega_{\mathbf{q}\nu}}} \sum_{pp'} e^{i(\mathbf{k}\cdot\mathbf{R}_p + \mathbf{q}\cdot\mathbf{R}_{p'})} \\ \times \sum_{m'n'\kappa\alpha} U_{mm'\mathbf{k}+\mathbf{q}} g_{m'n'\kappa\alpha}(\mathbf{R}_p, \mathbf{R}_{p'}) U_{n'n\mathbf{k}}^{\dagger} e_{\kappa\alpha,\nu}(\mathbf{q})$$



$$g_{mn\kappa\alpha}(\mathbf{R}_p, \mathbf{R}_{p'}) = \langle w_{m0}(\mathbf{r}) | \frac{\partial V_{\text{SCF}}}{\partial \tau_{\kappa\alpha}}(\mathbf{r} - \mathbf{R}_{p'}) | w_{n0}(\mathbf{r} - \mathbf{R}_p) \rangle_{\text{sc}}$$



Wannier interpolation of electron-phonon matrix elements


$$g_{mn\nu}(\mathbf{k}, \mathbf{q}) = \sqrt{\frac{\hbar}{2M_{\kappa}\omega_{\mathbf{q}\nu}}} \sum_{pp'} e^{i(\mathbf{k}\cdot\mathbf{R}_p + \mathbf{q}\cdot\mathbf{R}_{p'})} \\ \times \sum_{m'n'\kappa\alpha} U_{mm'\mathbf{k}+\mathbf{q}} g_{m'n'\kappa\alpha}(\mathbf{R}_p, \mathbf{R}_{p'}) U_{n'n\mathbf{k}}^{\dagger} e_{\kappa\alpha,\nu}(\mathbf{q})$$

$$g_{mn\kappa\alpha}(\mathbf{R}_p, \mathbf{R}_{p'}) = \langle w_{m0}(\mathbf{r}) | \frac{\partial V_{\text{SCF}}}{\partial \tau_{\kappa\alpha}}(\mathbf{r} - \mathbf{R}_{p'}) | w_{n0}(\mathbf{r} - \mathbf{R}_p) \rangle_{\text{sc}}$$



Figures from Giustino et al, Phys. Rev. B 76, 165108 (2007)

EPW software



Electron-phonon Wannier (EPW) is a free GPL Fortran software, part of Quantum-Espresso, that relies on maximally localized Wannier functions (MLWF) to interpolate electron-phonon matrix elements on ultra dense momentum grids.

The electron-phonon interaction in polar materials

The electron-phonon matrix element in polar materials

- Wannier interpolation in the presence of Fröhlich interactions

In polar materials, $g_{mn,\nu}(\mathbf{k}, \mathbf{q})$ diverges as $1/|\mathbf{q}|$ for $|\mathbf{q}| \rightarrow 0$

Split the electron-phonon matrix elements into a short- ($\mathcal{S}$) and a long-range ($\mathcal{L}$) contribution:

$$g(\mathbf{k}, \mathbf{q}) = g^{\mathcal{S}}(\mathbf{k}, \mathbf{q}) + g^{\mathcal{L}}(\mathbf{k}, \mathbf{q})$$

The electron-phonon matrix element in polar materials

- Wannier interpolation in the presence of Fröhlich interactions

In polar materials, $g_{mn,\nu}(\mathbf{k}, \mathbf{q})$ diverges as $1/|\mathbf{q}|$ for $|\mathbf{q}| \rightarrow 0$

Split the electron-phonon matrix elements into a short- ($\mathcal{S}$) and a long-range ($\mathcal{L}$) contribution:

$$g(\mathbf{k}, \mathbf{q}) = g^{\mathcal{S}}(\mathbf{k}, \mathbf{q}) + g^{\mathcal{L}}(\mathbf{k}, \mathbf{q})$$

$$g^{\mathcal{L}}(\mathbf{k}, \mathbf{q}) = i \frac{4\pi}{\Omega} \frac{e^2}{4\pi\epsilon_0} \sum_{\kappa} \left(\frac{\hbar}{2N_p M_{\kappa} \omega_{\mathbf{q}}} \right)^{\frac{1}{2}} \times \\ \sum_{\mathbf{G} \neq -\mathbf{q}} \frac{(\mathbf{q} + \mathbf{G}) \cdot \mathbf{Z}_{\kappa}^* \cdot \mathbf{e}_{\kappa}(\mathbf{q})}{(\mathbf{q} + \mathbf{G}) \cdot \boldsymbol{\epsilon}^{\infty} \cdot (\mathbf{q} + \mathbf{G})} \langle \psi_{\mathbf{k}+\mathbf{q}} | e^{i(\mathbf{q}+\mathbf{G}) \cdot (\mathbf{r}-\boldsymbol{\tau}_{\kappa})} | \psi_{\mathbf{k}} \rangle_{\text{sc}}$$

The electron-phonon matrix element in polar materials

- Wannier interpolation in the presence of Fröhlich interactions




Figure from Verdi and Giustino, Phys. Rev. Lett. 115, 176401 (2015)

The electron-phonon matrix element in polar materials

- Wannier interpolation in the presence of Fröhlich interactions





Figure from Verdi and Giustino, Phys. Rev. Lett. 115, 176401 (2015)


Phonon-mediated superconductivity

Phonon-mediated superconductivity




electron Cooper
pairs in a lattice


Phonon-mediated superconductivity




electron Cooper pairs in a lattice




exchange of virtual phonons produces an attraction for electrons close to Fermi level






Phonon-mediated superconductivity




electron Cooper pairs in a lattice




exchange of virtual phonons produces an attraction for electrons close to Fermi level







Phonon-mediated superconductivity



electron Cooper pairs in a lattice



exchange of virtual phonons produces an attraction for electrons close to Fermi level



Migdal-Eliashberg theory

paring self-energy

dressed phonon propagator

screened Coulomb interaction

$$\hat{\Sigma}_{n\mathbf{k}}(i\omega_j) = g_{nm\nu}(\mathbf{q}, \mathbf{k}) \overset{\substack{\text{dressed phonon propagator} \\ D_{\mathbf{q}\nu}(i\omega_j - i\omega_{j'})}}{\text{cloud}} \overset{\substack{\text{e-ph matrix elements} \\ \hat{G}_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}}{\text{line}} g_{mn\nu}(\mathbf{k}, \mathbf{q}) + \overset{\substack{\text{screened Coulomb interaction} \\ V_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(i\omega_j - i\omega_{j'})}}{\text{dashed arc}} \overset{\substack{\text{interacting Green's function} \\ \hat{G}_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}}{\text{line}}$$


e-ph matrix elements

interacting Green's function

Allen and Mitrović, Solid State Phys. 37, 1 (1982);

Margine and Giustino, Phys. Rev. B 87, 024505 (2013)

Migdal-Eliashberg theory



Migdal's theorem

Only the leading terms in Feynman diagram of the self-energy are included.

The neglected terms are of the order of $(m_e/M)^{1/2} \propto \omega_D/\epsilon_F$.

Allen and Mitrović, Solid State Phys. 37, 1 (1982);

Margine and Giustino, Phys. Rev. B 87, 024505 (2013)

Anisotropic Migdal-Eliashberg equations

$$\begin{aligned}
 Z_{n\mathbf{k}}(i\omega_j) &= 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\
 \text{mass renormalization} & \quad \times \lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F) \\
 \text{function} & \\
 Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) &= \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\
 \text{superconducting} & \quad \times [\lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F) \\
 \text{gap function} &
 \end{aligned}$$

Anisotropic Migdal-Eliashberg equations

$$\begin{aligned}
 Z_{n\mathbf{k}}(i\omega_j) &= 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\
 \text{mass renormalization} & \times \lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F) \\
 \text{function} & \\
 Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) &= \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\
 \text{superconducting} & \\
 \text{gap function} & \times [\lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)
 \end{aligned}$$

Anisotropic Migdal-Eliashberg equations

$$\begin{aligned}
 Z_{n\mathbf{k}}(i\omega_j) &= 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\
 \text{mass renormalization} & \times \lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F) \\
 \text{function} & \\
 Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) &= \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\
 \text{superconducting} & \\
 \text{gap function} & \times [\lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)
 \end{aligned}$$

$$\lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j) = N_F \sum_{\nu} \int_0^{\infty} d\omega \frac{2\omega}{\omega_j^2 + \omega^2} |g_{mn\nu}(\mathbf{k}, \mathbf{q})|^2 \delta(\omega - \omega_{\mathbf{q}\nu})$$

↑
anisotropic e-ph
coupling strength

Anisotropic Migdal-Eliashberg equations

$$\begin{aligned}
 Z_{n\mathbf{k}}(i\omega_j) &= 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\
 \text{mass renormalization} & \times \lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F) \\
 \text{function} & \\
 Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) &= \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\
 \text{superconducting} & \\
 \text{gap function} & \times [\lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)
 \end{aligned}$$

$$\lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j) = N_F \sum_{\nu} \int_0^{\infty} d\omega \frac{2\omega}{\omega_j^2 + \omega^2} |g_{mn\nu}(\mathbf{k}, \mathbf{q})|^2 \delta(\omega - \omega_{\mathbf{q}\nu})$$

↑
anisotropic e-ph
coupling strength

$i\omega_j = i(2j + 1)\pi T$ (j integer) are Matsubara frequencies

Anisotropic Migdal-Eliashberg equations

$$\begin{aligned} Z_{n\mathbf{k}}(i\omega_j) &= 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ &\quad \times \lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F) \\ Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) &= \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ &\quad \times [\lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F) \end{aligned}$$

Anisotropic Migdal-Eliashberg equations

$$Z_{n\mathbf{k}}(i\omega_j) = 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ \times \lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)$$

$$Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) = \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ \times [\lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)$$

- The coupled nonlinear equations need to be solved self-consistently at each **temperature T**

Anisotropic Migdal-Eliashberg equations

$$Z_{n\mathbf{k}}(i\omega_j) = 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ \times \lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)$$

$$Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) = \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ \times [\lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)$$

- The coupled nonlinear equations need to be solved self-consistently at each **temperature T**
- The equations must be evaluated on dense electron **$\mathbf{k}$ -** and phonon **$\mathbf{q}$ -meshes** to properly describe anisotropic effects

Anisotropic Migdal-Eliashberg equations

$$Z_{n\mathbf{k}}(i\omega_j) = 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ \times \lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)$$

$$Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) = \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ \times [\lambda_{n\mathbf{k},m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)$$

- The coupled nonlinear equations need to be solved self-consistently at each **temperature T**
- The equations must be evaluated on dense electron **$\mathbf{k}$ -** and phonon **$\mathbf{q}$ -meshes** to properly describe anisotropic effects
- The sum over **Matsubara frequencies** must be truncated (typically set to four to ten times the largest phonon energy)

Anisotropic Migdal-Eliashberg equations

$$Z_{n\mathbf{k}}(i\omega_j) = 1 + \frac{\pi T}{\omega_j N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\omega_{j'}}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ \times \lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)$$

$$Z_{n\mathbf{k}}(i\omega_j) \Delta_{n\mathbf{k}}(i\omega_j) = \frac{\pi T}{N_F} \sum_{mj'} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} \frac{\Delta_{m\mathbf{k}+\mathbf{q}}(i\omega_{j'})}{\sqrt{\omega_{j'}^2 + \Delta_{m\mathbf{k}+\mathbf{q}}^2(i\omega_{j'})}} \\ \times [\lambda_{n\mathbf{k}, m\mathbf{k}+\mathbf{q}}(\omega_j - \omega_{j'}) - \mu_c^*] \delta(\epsilon_{m\mathbf{k}+\mathbf{q}} - \epsilon_F)$$

- The coupled nonlinear equations need to be solved self-consistently at each **temperature T**
- The equations must be evaluated on dense electron **$\mathbf{k}$ -** and phonon **$\mathbf{q}$ -meshes** to properly describe anisotropic effects
- The sum over **Matsubara frequencies** must be truncated (typically set to four to ten times the largest phonon energy)
- $Z_{n\mathbf{k}}$ and $\Delta_{n\mathbf{k}}$ are only meaningful for **$n\mathbf{k}$ at or near the Fermi surface**

Superconductivity in 2H-NbS₂

Scanning tunneling spectra of 2H-NbS₂






Figure from Guillaumón et al, Phys. Rev. Lett. 101, 166407 (2008)


Superconductivity in 2H-NbS₂




Superconductivity in 2H-NbS₂




Superconductivity in 2H-NbS₂



Superconductivity in 2H-NbS₂




Superconductivity in 2H-NbS₂





Superconductivity in 2H-NbS₂

- Anisotropic Migdal-Eliasbergh formalism with *ab initio* Coulomb pseudopotential $\mu_c^* = 0.2$ (EPW and SternheimerGW)




Superconductivity in 2H-NbS₂

- Anisotropic Migdal-Eliasbergh formalism with *ab initio* Coulomb pseudopotential $\mu_c^* = 0.2$ (EPW and SternheimerGW)



Phonon-limited carrier transport

Carrier transport



- Lattice scattering
- Impurity scattering
- Ionized impurity scattering

Electric current and mobility

- The steady-state electric current $\mathbf{J}$ is related to the driving electric field $\mathbf{E}$ via the mobility tensors $\boldsymbol{\mu}$ as:

$$J_{\alpha} = e (n_e \mu_{e,\alpha\beta} + n_h \mu_{h,\alpha\beta}) E_{\beta} = -e \Omega^{-1} \sum_n \Omega_{\text{BZ}}^{-1} \int d\mathbf{k} f_{n\mathbf{k}} v_{n\mathbf{k},\alpha}$$

where $v_{n\mathbf{k},\alpha} = \hbar^{-1} \partial \varepsilon_{n\mathbf{k}} / \partial k_{\alpha}$ is the band velocity.

- We need to find the occupation function $f_{n\mathbf{k}}$ which reduces to the Fermi-Dirac distribution $f_{n\mathbf{k}}^0$ in the absence of the electric field

Electric current and mobility

- The steady-state electric current $\mathbf{J}$ is related to the driving electric field $\mathbf{E}$ via the mobility tensors $\boldsymbol{\mu}$ as:

$$J_\alpha = e (n_e \mu_{e,\alpha\beta} + n_h \mu_{h,\alpha\beta}) E_\beta = -e \Omega^{-1} \sum_n \Omega_{\text{BZ}}^{-1} \int d\mathbf{k} f_{n\mathbf{k}} v_{n\mathbf{k},\alpha}$$

where $v_{n\mathbf{k},\alpha} = \hbar^{-1} \partial \varepsilon_{n\mathbf{k}} / \partial k_\alpha$ is the band velocity.

- We need to find the occupation function $f_{n\mathbf{k}}$ which reduces to the Fermi-Dirac distribution $f_{n\mathbf{k}}^0$ in the absence of the electric field
- The mobility is defined as:

$$\mu_{e,\alpha\beta} = \frac{\sigma_{\alpha\beta}}{n_e} = \frac{1}{n_e} \frac{\partial J_\alpha}{\partial E_\beta} = - \sum_{n \in \text{CB}} \int d\mathbf{k} v_{n\mathbf{k},\alpha} \partial_{E_\beta} f_{n\mathbf{k}} / \sum_{n \in \text{CB}} \int d\mathbf{k} f_{n\mathbf{k}}^0$$

- We need to evaluate the linear response of the distribution function $f_{n\mathbf{k}}$ to the electric field $\mathbf{E}$.

Boltzmann transport equation

$$\left. \frac{\partial f_{n\mathbf{k}}(T)}{\partial t} \right|_{\text{scatt}} = (-e)\mathbf{E} \cdot \frac{\partial f_{n\mathbf{k}}(T)}{\partial \mathbf{k}}$$

Boltzmann transport equation

$$\left. \frac{\partial f_{n\mathbf{k}}(T)}{\partial t} \right|_{\text{scatt}} = (-e)\mathbf{E} \cdot \frac{\partial f_{n\mathbf{k}}(T)}{\partial \mathbf{k}}$$


The right-hand side is the collisionless term of Boltzmann's equation for a uniform and constant electric field, in the absence of temperature gradients and magnetic fields

Boltzmann transport equation

$$\left. \frac{\partial f_{n\mathbf{k}}(T)}{\partial t} \right|_{\text{scatt}} = (-e)\mathbf{E} \cdot \frac{\partial f_{n\mathbf{k}}(T)}{\partial \mathbf{k}}$$

The right-hand side is the collisionless term of Boltzmann's equation for a uniform and constant electric field, in the absence of temperature gradients and magnetic fields

This left-hand side is the modification of the distribution function arising from electron-phonon scattering in and out of the state $|n\mathbf{k}\rangle$, via emission or absorption of phonons with frequency $\omega_{q\nu}$



Linearized Boltzmann transport equation

We expand $f_{n\mathbf{k}}$ into $f_{n\mathbf{k}} = f_{n\mathbf{k}}^0 + \mathcal{O}(\mathbf{E})$ for small $\mathbf{E}$ and keep only the linear term in $\mathbf{E}$ to get

$$(-e)\mathbf{E} \cdot \frac{\partial f_{n\mathbf{k}}(T)}{\partial \mathbf{k}} = (-e)\mathbf{E} \cdot \mathbf{v}_{n\mathbf{k}} \frac{\partial f_{n\mathbf{k}}^0}{\partial \varepsilon_{n\mathbf{k}}}$$

$$\begin{aligned} \frac{\partial f_{n\mathbf{k}}^0}{\partial \varepsilon_{n\mathbf{k}}} \mathbf{v}_{n\mathbf{k}} \cdot (-e)\mathbf{E} &= \frac{2\pi}{\hbar} \sum_{m\nu} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} |g_{mn\nu}(\mathbf{k}, \mathbf{q})|^2 \\ &\times \left\{ (1 - f_{n\mathbf{k}}) f_{m\mathbf{k}+\mathbf{q}} \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}} + \hbar\omega_{\mathbf{q}\nu}) (1 + n_{\mathbf{q}\nu}) \right. \\ &\quad + (1 - f_{n\mathbf{k}}) f_{m\mathbf{k}+\mathbf{q}} \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}} - \hbar\omega_{\mathbf{q}\nu}) n_{\mathbf{q}\nu} \\ &\quad - f_{n\mathbf{k}} (1 - f_{m\mathbf{k}+\mathbf{q}}) \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}} - \hbar\omega_{\mathbf{q}\nu}) (1 + n_{\mathbf{q}\nu}) \\ &\quad \left. - f_{n\mathbf{k}} (1 - f_{m\mathbf{k}+\mathbf{q}}) \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}} + \hbar\omega_{\mathbf{q}\nu}) n_{\mathbf{q}\nu} \right\} \end{aligned}$$

Linearized Boltzmann transport equation

We take the derivatives of the Boltzmann equation with respect to $\mathbf{E}$ to obtain the iterative Boltzmann transport equation (IBTE):

$$\begin{aligned}\partial_{E_\beta} f_{n\mathbf{k}} = & e \frac{\partial f_{n\mathbf{k}}^0}{\partial \varepsilon_{n\mathbf{k}}} v_{n\mathbf{k},\beta} \tau_{n\mathbf{k}}^0 + \frac{2\pi \tau_{n\mathbf{k}}^0}{\hbar} \sum_{m\nu} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} |g_{m\nu}(\mathbf{k}, \mathbf{q})|^2 \\ & \times \left[(1 + n_{\mathbf{q}\nu} - f_{n\mathbf{k}}^0) \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}} + \hbar\omega_{\mathbf{q}\nu}) \right. \\ & \left. + (n_{\mathbf{q}\nu} + f_{n\mathbf{k}}^0) \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}} - \hbar\omega_{\mathbf{q}\nu}) \right] \partial_{E_\beta} f_{m\mathbf{k}+\mathbf{q}}\end{aligned}$$

having defined the relaxation time:

$$\begin{aligned}\frac{1}{\tau_{n\mathbf{k}}^0} = & \frac{2\pi}{\hbar} \sum_{m\nu} \int \frac{d\mathbf{q}}{\Omega_{\text{BZ}}} |g_{m\nu}(\mathbf{k}, \mathbf{q})|^2 \\ & \times \left[(1 - f_{m\mathbf{k}+\mathbf{q}}^0 + n_{\mathbf{q}\nu}) \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}} - \hbar\omega_{\mathbf{q}\nu}) \right. \\ & \left. + (f_{m\mathbf{k}+\mathbf{q}}^0 + n_{\mathbf{q}\nu}) \delta(\varepsilon_{n\mathbf{k}} - \varepsilon_{m\mathbf{k}+\mathbf{q}} + \hbar\omega_{\mathbf{q}\nu}) \right]\end{aligned}$$

Self-energy relaxation time approximation (SERTA)

We can approximate IBTE by neglecting $\partial_{E_\beta} f_{m\mathbf{k}+\mathbf{q}}$


$$\partial_{E_\beta} f_{n\mathbf{k}} = e \frac{\partial f_{n\mathbf{k}}^0}{\partial \varepsilon_{n\mathbf{k}}} v_{n\mathbf{k},\beta} \tau_{n\mathbf{k}}^0$$

The intrinsic electron mobility is therefore:

$$\begin{aligned} \mu_{e,\alpha\beta} &= - \sum_{n \in \text{CB}} \int d\mathbf{k} \, v_{n\mathbf{k},\alpha} \partial_{E_\beta} f_{n\mathbf{k}} / \sum_{n \in \text{CB}} \int d\mathbf{k} \, f_{n\mathbf{k}}^0 \\ &= \frac{-e}{n_e \Omega} \sum_{n \in \text{CB}} \int \frac{d\mathbf{k}}{\Omega_{\text{BZ}}} \frac{\partial f_{n\mathbf{k}}^0}{\partial \varepsilon_{n\mathbf{k}}} v_{n\mathbf{k},\alpha} v_{n\mathbf{k},\beta} \tau_{n\mathbf{k}}^0 \end{aligned}$$



Intrinsic carrier mobility in Si

Electron and hole mobility in silicon (EPW)





Intrinsic carrier mobility in Si

Electron and hole mobility in silicon (EPW)




Intrinsic carrier mobility in GaN

Electron and hole mobility in GaN (EPW)



Route to high mobility in GaN

Crystal-field engineering of band structure and mobility in GaN



EPW capabilities



- electron and phonon linewidths, scattering rates, and lifetimes
- electron and phonon spectral functions
- electron-phonon vertex in the presence of Fröhlich interactions (polar materials)
- electron-phonon coupling strength
- phonon-limited optical absorption
- anisotropic superconducting properties
- electronic transport properties (mobility and resistivity)



Features:

- Supports LDA/GGA functionals
- Supports NC and US pseudopotentials
- Supports spin-orbit coupling
- Supports time-reversal symmetry
- Polar divergence correctly interpolated
- Integrated into QE and rely on Wannier90
- MPI parallelization
- Has a test-farm for stability and portability of the code

EPW outlook



- mobility at finite magnetic field
- e-ph interactions in 2D materials
- high-throughput e-ph computations with AiiDA
- parallelization over G-vectors
- spin-transport
- fully ab initio Migdal-Eliashberg approach for superconductivity



<http://epw.org.uk>




<https://gitlab.com/QEF/q-e>

Acknowledgments



Samuel Poncé
EPFL
Lausanne



Carla Verdi
University of
Vienna




Feliciano Giustino
University of Texas
at Austin

Acknowledgments



Samuel Poncé
EPFL
Lausanne



Carla Verdi
University of
Vienna



Feliciano Giustino
University of Texas
at Austin



References methodology

- F. Giustino, M. L. Cohen, and S. G. Louie, Phys. Rev. B 76, 165108 (2007) [\[link\]](#)
- E. R. Margine and F. Giustino, Phys. Rev. B 87, 024505 (2013) [\[link\]](#)
- C. Verdi and F. Giustino, Phys. Rev. Lett. 115 (17), 176401 (2015) [\[link\]](#)
- F. Giustino, Rev. Mod. Phys. 89, 015003 (2017) [\[link\]](#)
- S. Poncé, E. R. Margine, and F. Giustino, Phys. Rev. B 97, 121201(R) (2018) [\[link\]](#)
- S. Poncé, W. Li, S. Reichardt, and F. Giustino, Rep. Prog. Phys. 83, 036501 (2020) [\[link\]](#)
- S. Baroni, S. de Gironcoli, A. Dal Corso, P. Giannozzi, Rev. Mod. Phys. 73, 515 (2001) [\[link\]](#)
- N. Marzari, A. A. Mostofi, J. R. Yates, I. Souza, D. Vanderbilt, Rev. Mod. Phys. 84, 1419 (2012) [\[link\]](#)

References software

- S. Poncé, E. R. Margine, C. Verdi, and F. Giustino, Comput. Phys. Commun. 209, 116 (2016) [\[link\]](#)
- P. Giannozzi et al., J.Phys.:Condens.Matter 29, 465901 (2017) [\[link\]](#)
- G. Pizzi et al., J. Phys.: Condens. Matter 32, 165902 (2020) [\[link\]](#)

References applications

- C. Heil, S. Poncé, H. Lambert, M. Schlipf, E. R. Margine, and F. Giustino, Phys. Rev. Lett., 119, 087003 (2017) [\[link\]](#)
- M. Gao, Q.-Z. Li, X.-W. Yan, and J. Wang, Phys. Rev. B 95, 024505 (2017) [\[link\]](#)
- F. Zheng and J. Feng, Phys. Rev. B 99, 161119(R) (2019) [\[link\]](#)
- T.-H. Liu, J. Zhou, B. Liao, D. J. Singh, and G. Chen, Phys. Rev. B 95, 075206 (2017) [\[link\]](#)
- S. Poncé, D. Jena, and F. Giustino, Phys. Rev. Lett. 123, 096602 (2019) [\[link\]](#)
- M. Schlipf, S. Poncé, and F. Giustino, Phys. Rev. Lett. 121, 086402 (2018) [\[link\]](#)